


Soft PVC hose with polyester yarn reinforcement, for delivery of cooling liquids, chemical solutions, food and compressed air



Ø nominal mm	Ø nominal inch	Ø i.d. mm	Ø o.d. mm	working pressure at 23° bar	working press. at 40° bar	working press. at 60° bar	bursting press. at 23° bar	bending radius mm	total thickness mm	weight meter g/m	# wires for angle n° x a°	coil length m	Availability
4		4	10	20	16	12	60	12	3	80	12x45°	100	On demand
5	3/16	5	11	20	16	12	60	15	3	90	12x45°	100	On demand
6	1/4	6	11	20	16	12	60	19	2.5	80	12x50°	100	On demand
6	1/4	6	12	20	16	12	60	17	3	105	12x54°	100	On demand
6	1/4	6	14	20	16	12	60	15	4	145	12x50°	100	On demand
7		7	13	20	16	12	60	20	3	115	16x45°	100	On demand
8	5/16	8	13	18	13	9	54	28	2.5	105	16x50°	100	On demand
10	3/8	10	15	18	13	9	54	36	2.5	120	18x50°	100	On demand
10	3/8	10	16	18	13	9	54	30	3	150	18x54°	100	On demand
12		12	17	12	9	6	36	35	2.5	140	18x52°	50	On demand
12		12	18	12	9	6	36	35	3	180	18x52°	50	On demand
13	1/2	13	18	12	9	6	36	43	2.5	150	18x52°	50	On demand
13	1/2	13	19	12	9	6	36	52	3	175	18x52°	50	On demand
15		15	21	10	7	4	30	60	3	215	24x50°	50	On demand
15		15	23	10	7	4	30	60	4	280	24x50°	50	On demand
16	5/8	16	21	10	7	4	30	62	2.5	185	24x50°	50	On demand
16	5/8	16	22	10	7	4	30	60	3	210	24x50°	50	On demand
19	3/4	19	25	10	7	4	30	70	3	260	24x54°	50	On demand
19	3/4	19	26	10	7	4	30	70	3.5	300	24x54°	50	On demand
22		22	30	8	5	3	24	85	4	420	24x54°	50	On demand
25	1	25	32	8	5	3	24	150	3.5	390	24x54°	50	On demand
25	1	25	33	8	5	3	24	110	4	450	24x54°	50	On demand
30		30	38	8	5	3	24	170	4	560	24x54°	50	On demand
32	1 1/4	32	42	8	4	2	24	200	5	700	36x50°	50	On demand
35		35	45	8	4	2	24	250	5	750	36x54°	50	On demand
38	1 1/2	38	48	8	4	2	24	300	5	850	48x54°	50	On demand
40		40	50	8	4	2	24	350	5	880	48x54°	50	On demand
50	2	50	62	8	4	2	24	450	6	1350	48x54°	25	On demand